

**GRAPHICS** - Wide Format Ink Jet Print Media

 Issue date : 05/01/2005  
 Date last modification : 19/03/2019

## 4-GL3B-02996 RI-JET 140 FLOOR TALKER GLOSS WHITE AR886 REMOVABLE GREY WKPE144

### Face Material

Gloss white monomeric vinyl.

Type	Monomeric vinyl	
Colour and Finish	Gloss white	
Weight	134 g/m <sup>2</sup> ±10%	ISO-536
Thickness	100 µ ±10%	ISO 534-80

### Adhesive

Removable acrylic adhesive featuring good water and cleaning agents resistance. High adhesion on a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP). The grey pigmentation of the adhesive gives to the material excellent coverage performances. Ideal for floor graphics.

Reference	AR886 removable	
Type	Acrylic removable	
Min. Appl. Temp.	+10°C	
Service Temp.	-20°C/+140°C	
Shear	Very High	
Tack	High N/inch <sup>2</sup>	
Final Adhesion	Very High N/inch	

### Liner

Type	Siliconised two side PE Kraft	
Colour and Finish	White	
Weight	144 g/m <sup>2</sup> ±10%	PP-032 - ISO 536
Thickness	155 µ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

### Applications

Advertising and promotional applications, designed to be applied to waxed commercial PVC and ceramic tile floor surfaces. To use in combination with the overlaminating film RI-121/200 FLOOR TALKER.

Furthermore, the product guarantees a clean removability, leaving the application surface without any adhesive residue even using a permanent adhesive.

- . Flammability: Self - extinguish (ISO-3795)
  - . Outdoor vertical exposure durability: UP TO 3 YEARS.
- The Durability data are given for unprinted films only and based on Zone 1 exposure conditions (Northern and Eastern Europe, Italy, France).

### Printing Methods

The RI-JET series of ink-jet print media gives excellent print results with UV, latex, solvent and eco-solvent ink-jet printing and with solvent based screenprinting.

Testing for suitability between media, printers and inks is always recommended prior to use.

### Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

