

50.001N-2 | Crystal Clear (Removable)

TOTAL GLASS | Clear Printable Media

Features

50.001N-2 | Crystal Clear (Removable) has been specifically designed for the production of window graphics. The crystal clear 75 micron polymeric PVC face-stock film, the ultra-clear solvent based removable adhesive system and the polyester liner allow the film to be almost invisible when applied. 50.001N-2 is printable with (eco)solvent, UV and latex inks.

The face film has been coated with a removable adhesive and is designed for short term indoor and outdoor applications on flat and slightly curved surfaces. The matt stable PET liner is directed to LFP purposes. There will be no adhesive residue when removing the film up to one year after the application.

50.001N-2 | Crystal Clear (Removable) is available in 1520mm (width) x 50m (length) rolls.

Technical & Performance Information

Film Thickness	75 micron
Adhesive Thickness	25 micron
Total Thickness	100 micron
Adhesive type	Removable clear solvent based acrylic
Release Liner	100 micron PET neutral liner
Artificial Weathering *	5 years (unprinted)
Adhesion to steel (20 mins / 180°)	3 N/25mm
Adhesion to steel (24 hrs / 180°)	3 N/25mm
Dimensional Stability	Very good
Application Temperature	+5°C to +25°C
Service Temperature	-40°C to +95°C

* equivalent to vertical exposure in Mid-European climate

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.