

Ri-Mark Translucent

PRODUCT DESCRIPTION / BENEFITS Ri-Mark Translucent is the ideal choice for illuminated signage.

The matt translucent polymeric vinyl, UV stabilised, is manufactured in such a way to ensure a uniform colour appearance and have an external colour stability up to 7 years. The very cohesive solvent-based adhesive provides an excellent dimensional stability and water resistance. The kraft liner is designed for trouble-free plotter cutting on a wide variety of computerised sign cutting equipment.

All our products are REACH & RoHS compliant.

TYPICAL USE

- Long term indoor and outdoor illuminate signage.
- Windows graphics

CONSTRUCTION

- **Face film:** 80 µm matt calendered polymeric vinyl
- **Adhesive:** permanent clear solvent-based acrylic
- **Release liner:** clay coated kraft paper 120 g/m²

CONVERTING METHOD

Specially developed for trouble-free plotter cutting on a wide variety of computerised sign cutting equipment.

APPLICATION METHOD / INSTRUCTIONS FOR USE

Ri-Mark Translucent films are suitable for dry and wet application method.
It is possible to thermoform Ri-Mark Translucent film if applied on acrylic panels.
Application temperature above 10°C, on clean and degreased substrates.

EXPECTED DURABILITY

The expected vertical outdoor durability in Central Europe (zone 1) is:

- 7 years for all colours
- 5 years for metallic films

This information is based on real file experience and artificial aging according to ISO 4892-2.

Note: Exposure to severe temperature and ultra-violet light will cause a quicker deterioration. This applies also to polluted area, high altitude, horizontal applications, and south-facing exposure in north hemisphere.

SHELF LIFE

Shelf life is 2 years, when stored at 23 °C and 50 % relative humidity conditions.
Higher temperatures and/or humidity levels will reduce product shelf life.

Ri-Mark Translucent

PHYSICO-CHEMICAL PROPERTIES / TYPICAL VALUES

Face thickness all colours, without adhesive Translucent 698 Light Stop	80 µm 130 µm	ISO 534-80
Face thickness all colours, with adhesive Translucent 698 Light Stop	100 µm 150 µm	ISO 534-80
Tensile strength (machine direction)	> 14 N/cm	ISO 527
Elongation at break (machine direction)	>150%	ISO 527
Fire resistance on aluminium	Self-extinguishing	ISO 3795:1989
Dimensional stability (1 week @70 °C on glass)	0,2 mm	FTM 14
Initial adhesion on glass (20 minutes)	13 N/25mm	FTM 1
Adhesion on glass (24 hours)	16 N/25mm	FTM 1
Final adhesion on glass (1 week)	18 N/25mm	FTM 1
Minimum application temperature	+10 °C	
Service temperature	From -40 °C to +90 °C	
One side siliconized clay coated paper liner	120 g/m ²	ISO 536
Humidity resistance	No effect	200 hours exposure
Water resistance	No effect	24 hours immersion
Detergent (1% solution)	No effect	24 hours immersion
Isopropyl alcohol / Water (20/80)	No effect	10 minutes immersion

QUALITY CERTIFICATION



DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.